


KLINGER TOPLINE K4311



Aramid & PTFE yarn hybrid packing



GENERAL PROPERTIES

- » Suitable for water, oil, solvents, and weak acids and alkalis.
- » The PTFE element, which is K4311's running surface, is soft and forgiving. Shaft wear is therefore kept to a minimum.
- » The strong aramid corner posts resist extrusion from the stuffing box while ensuring that unwanted particles are excluded. This reduces the detrimental effects of abrasive and viscous media.


TopLine hybrid packing that combines the properties of Aramid and PTFE resulting in an excellent dynamic packing for rotary and reciprocating duties.

K4311 is manufactured from a combination of aramid and PTFE yarns using the KLINGERlock braiding technique. The result is a packing with high resistance to extrusion that will operate at high peripheral speeds.

KLINGER TopLine packing range has been selected to provide users with gland sealing products that meet today's demanding services, offering effective and trouble-free sealing during application. To achieve this goal we have selected the best materials and the best production methods.

AVAILABILITY

SIZE (MM)	LENGTH (M)	SIZE (MM)	LENGTH (M)
3.2 x 3.2	8	12.5 x 12.5	8
5.0 x 5.0	8	14.0 x 14.0	8
6.5 x 6.5	8	16.0 x 16.0	8
8.0 x 8.0	8	19.0 x 19.0	8
9.5 x 9.5	8	22.0 x 22.0	8
11.0 x 11.0	8	25.0 x 25.0	8



APPLICATION GUIDELINES

- ① Caution: May be suitable but essential that you refer to KLINGER for advice.
- ② Usually satisfactory, but suggest you refer to KLINGER for advice.
- ③ Usually satisfactory to use without reference.

NOTE: Chemical compatibility must be considered in all cases.

TYPICAL SPECIFICATIONS

PROPERTIES	VALUES
min. temperature	-100 °C
max. steam temperature	280 °C
max. temperature	280 °C
max. static pressure	250 bar
max. rotary pressure	30 bar
max. reciprocating pressure	150 bar
max. speed	6 m/s
pH range	2-12

This packing should not be subjected to maximums of temperature, pressure and speed simultaneously.

KLINGER Portugal, Lda.
 Via José Régio, 36
 Centro Empresarial Vilar do Pinheiro
 4485-860 - Vila do Conde
 T: +351 229 470 910
 Email: geral@klinger.pt

