


KLINGER TOPLINE K54S



PTFE filament packing



GENERAL PROPERTIES


- » Virtually resistant to all media including strong acids and alkalis.
- » K54S is manufactured from PTFE filaments added with a PTFE lubricant.
- » KLINGERlock braiding process ensures a firm but flexible product of consistent density.
- » Due to its diverse capabilities K54S offers the engineer a packing that can cut maintenance requirements and also reduce stock holdings.
- » Most glands packed with K54S need little adjustment after initial installation.

An excellent choice for plant wide use on services to 260 °C and 200 bar, especially when a high level of resistance to chemical attack is required.

KLINGER TopLine packing range has been selected to provide users with gland sealing products that meet today's demanding services, offering effective and trouble-free sealing during application. To achieve this goal we have selected the best materials and the best production methods.

AVAILABILITY

SIZE (MM)	LENGTH (M)	SIZE (MM)	LENGTH (M)
3.2 x 3.2	8	12.5 x 12.5	8
5.0 x 5.0	8	14.0 x 14.0	8
6.5 x 6.5	8	16.0 x 16.0	8
8.0 x 8.0	8	19.0 x 19.0	8
9.5 x 9.5	8	22.0 x 22.0	8
11.0 x 11.0	8	25.0 x 25.0	8



APPLICATION GUIDELINES

- ① Caution: May be suitable but essential that you refer to KLINGER for advice.
- ② Usually satisfactory, but suggest you refer to KLINGER for advice.
- ③ Usually satisfactory to use without reference.

NOTE: Chemical compatibility must be considered in all cases.

TYPICAL SPECIFICATIONS

PROPERTIES	VALUES
min. temperature	-240 °C
max. steam temperature	280 °C
max. temperature	280 °C
max. static pressure	200 bar
max. speed	5 m/s
pH range	0 – 14

This packing should not be subjected to maximums of temperature, pressure and speed simultaneously.

